

PRODUCT DATA

ALKYTHANE 7500

DESCRIPTION

RUST-OLEUM® Alkythane 7500 coatings are based on a urethane modified alkyd, providing good drying properties at low temperatures. The coatings are lead- and chromate-free and contains rust-inhibitive pigments (except for 7510 clear) for additional protection. The product is mould and algae resistant (except for 7510 Clear).

RECOMMENDED USES

RUST-OLEUM Alkythane 7500 should be applied on metal surfaces primed with RUST-OLEUM Alkyd primers. RUST-OLEUM Alkythane 7500 is intended for brush and roller application and can also be applied by spray. On properly primed or previously coated surfaces RUST-OLEUM Alkythane 7500 offers corrosion protection in a light industrial environment. For metal structures in a more aggressive industrial environment, application of an additional RUST-OLEUM Alkyd primer or Alkythane 7500 finish is recommended.

TECHNICAL DATA

Finish: high gloss*
 Colour: see colour card
 *7578 flat black and 7590 flat white
 7510 clear
 Density: 1.07 kg/l. ± 0.1 depending on colour
 Solids content: 52.5% by volume ± 2.0 depending on colour
 Viscosity: 105 - 110 KU / Krebs Stormer Units at 20°C
 Recommended film thickness: 50 µm dry, equals 95 µm wet

Drying times: According to ASTM D1640-69

	at 20°C/50% r.h.	at 5°C/60% r.h.	at 30°C/50% r.h.
To touch :	2 hours	3 hours	1½ hour
Tack-free:	4 hours	6 hours	3 hours
To handle:	8 hours	16 hours	6 hours
To recoat:	after 16 hours	after 24 hours	after 8 hours
Full hardness:	7 days	14 days	5 days

Heat resistance: 90°C (dry heat), at elevated temperatures discoloration may occur

COVERAGE

Theoretical: 10.5 m²/l at 50 µm dry, depending on colour.
 Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE

Remove oil, grease and all other contamination by alkaline or high pressure (steam) PREPARATION cleaning in combination with appropriate detergents. Remove rust scale, loose mill scale, loose rust and loose coatings by scraping and wire brushing to St 2/3 (ISO 8501-1 : 1988), blast cleaning to Sa 2½ (ISO 8501-1 : 1988) or sanding, followed by priming with the recommended RUST-OLEUM Primers. Sand previous coatings in good condition to provide a key for adhesion and check compatibility. The surface must be clean and dry during application.

DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION & THINNING

Brush up to 10 vol. % with RUST-OLEUM Thinner 633
 Use natural bristles, long hair brushes

PRODUCT DATA

ALKYTHANE 7500

APPLICATION & THINNING (continued)

Roller up to 10 vol. % with RUST-OLEUM Thinner 633
Use short nap, perlon 8 or mohair 4 -6 mm rollers
Roller application may require 2 coats to achieve the recommended dry film thickness.

Air-atomised spray: 10 to 30 vol. % with RUST-OLEUM Thinner 641
Gravity cup and pressure cup
Tip size: 1.0 - 1.5 mm Atomising pressure: 2 - 4 bar

Airless spray: up to 20 vol. % with RUST-OLEUM Thinner 641
Pneumatic and electric airless equipment
Tip size: 0.009-0.013 inch Fluid pressure: 150 - 200 bar
Check wet film thickness, avoid excessive film thickness

Clean-up use RUST-OLEUM Thinner 160 or mineral spirits

APPLICATION CONDITIONS

Temperature of air, substrate and coating material between 5 and 35°C and relative humidity below 85%.
The substrate temperature must be at least 3°C above dew point.

REMARKS

Maximum dry film thickness per coat: 80µm dry, equals 150 µm wet.

SHELF-LIFE/ CONDITIONS

5 years from date of production in unopened cans, if stored in dry, well ventilated areas, STORAGE not in direct sunlight at temperatures between 5° and 35°C.

The information contained herein is given in good faith. However, since application conditions are beyond our control, Rust-Oleum Netherlands B.V. cannot assume responsibility for any risks or liabilities which may result from the use of the products. The company reserves the right to modify data without prior notice.

Rust-Oleum Netherlands B.V.

Postbus 138
4700 AC Roosendaal
Nederland
Tel. +31 (0) 165-593 636
Fax +31 (0) 165-593 600
e-mail: ro_service@rust-oleum.nl
www.rust-oleum.nl

Rust-Oleum France S.A.

11, Rue Jules Verne, B.P.39
95322 ST-LEU-LA-FORET CEDEX
France
Tél. +33 (0) 1 30 40 00 44
Fax +33 (0) 1 30 40 99 80
e-mail: tmassonn@rust-oleum.fr
www.rust-oleum.nl

Rust-Oleum UK Ltd.

Unit 5D Alexandra Way Ashchurch B. Centre
Tewkesbury GL20 8NB
United Kingdom
Tel. +44 (0) 1684 - 27 33 33
Fax +44 (0) 1684 - 27 33 31
e-mail: info@rustoleum.co.uk
www.rust-oleum.nl

N.V. Mathys S.A.

B-3545 Zelem
Belgium
Tel. +32 (0) 13 460 200
Fax +32 (0) 13 460 201
e-mail: info@mathys.be
www.mathys.be