

RUST-OLEUM®
INDUSTRIAL



5401WB EPOXY IMPREGNATION PRIMER

Improves adhesion on porous mineral floors

- Impregnation of porous and brittle floors
- Can be applied on slightly damp surfaces
- Waterbased



KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

5401WB EPOXY IMPREGNATION PRIMER

DESCRIPTION

Waterbased epoxy impregnation primer for concrete and other porous, mineral surfaces.

RECOMMENDED USE

Impregnation Primer 5401WB is designed for application on concrete and masonry and is primarily intended for roller and brush application. Provides a good key for adhesion on porous, mineral substrates prior to the application RUST-OLEUM Pegakote or 9200 Rust-O-Thane.

TECHNICAL DATA

Density (g/cm ³):	1.04
Gloss Level:	Gloss
Solids Content in weight:	38%
Solids content in volume:	36%
Mixing Ratio:	Base : Activator = 4 : 1 (Volume)

DRY TIMES BY 20° C/RH 50%

Touch dry:	6 hours (20°C)
Dry to handle:	8 hours (20°C)
Dry to recoat:	min 8 hours, max 72 hours (20°C)
Fully cured:	72 hours (20°C)
Pot Life:	2 hours (20°C)
Induction Time:	5 minutes (20°C)

RECOMMENDED WET FILM THICKNESS

80 µm

RECOMMENDED DRY FILM THICKNESS

30 µm

THEORETICAL CONSUMPTION

12 m²/l

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

New concrete should cure and dry for at least 30 days prior to the application of the product. Remove oil, grease and all other surface contaminations by alkaline or high pressure-(steam)cleaning in combination with appropriate detergents. Remove all laitance, loose or unsound concrete by vacuum-blasting or etching with Surfa-Etch 108 Etching Solution. Remove concrete curing compounds completely. Large surfaces should preferably be prepared by abrasive blasting (vacuum blasting) or flame cleaning. Profile maximum 0.5mm. Defects in the concrete should be repaired with 5180 Epoxy Repair Mortar. Small (hair) cracks and air-pockets should be repaired with Epoxy Putty 5412. The surface should be clean and dry during application.

DIRECTIONS FOR USE

Stir individual components thoroughly before mixing them together. Use a low speed mixer in combination with the boxing method.

APPLICATION CONDITIONS

Temperature of air and substrate between 10 and 35°C and relative humidity below 85%.

APPLICATION & THINNING: BRUSH

Use natural bristles, longhair brushes.

APPLICATION & THINNING: ROLLER

Use medium nap, 12 mm, polyester rollers. For textured surfaces use long nap 14-18 mm rollers.

CLEANING OF EQUIPMENT / SPILLS

Water

REMARKS

Food should be stored separately or covered adequately during application of the Impregnation Primer 5401WB

SAFETY DATA

VOC level:	65 g/l
VOC category:	A/j
VOC limit:	140 g/l
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

SHELF LIFE

Minimum of 3 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 22/11/2023

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu